

Reliability Monitoring Results

Quarters: Q1/2022 to Q4/2022 Based on structural similarity

SupplierUser Part NumberNexperia B.V.74AUP1G04GW-Q100

Part Description: Single inverter

Function Family: AUP Process family: C075 Package family: TSSOP

| JESD47 | ' Test | Test Conditions | Duration | # Lots | # Quantity | # Rejects |
|--------|--|---|-----------------------------|-----------|------------|--------------|
| # 1 | TEST Pre- and Post-Stress Electrical Test | Tamb = 25 °C | N/A | see below | all parts | see below |
| # 2 | PC Preconditioning | JESD22-A113 MSL 1 | N/A | 1070 | 83683 | 0 |
| # 5a | HTOL EFR High Temperature Operating Life Extrinsic | JESD22-A108 Tj = 150°C $V_{CCMAX} \le V \le 1.2*V_{CCMAX}$ | 48 hours or 168 hours | 240 | 41981 | 0 |
| # 5b | HTOL IFR High Temperature Operating Life Intrinsic | JESD22-A108 Tj = 150°C $V_{CCMAX} \le V \le 1.2*V_{CCMAX}$ | ≥500 hours | 99 | 7448 | 0 |
| # 7 | TC Temperature Cycling | JESD22-A104 -65 °C to 150°C | ≥500 cycles | 549 | 43127 | 0 |
| # 9 | uHAST / HAST unbiased or biased High Accelerated Stress Test | JESD22-A101 Tamb = 130 °C, RH = 85%, V = V _{CCMAX} | 96 hours | 521 | 40556 | 0 |

Calculation of PPM, FIT and MTTF

Test considered for PPM calculation: High Temperature Operating LifeTest Extrinsic (HTOL EFR, Test # 5a above) Test considered for FIT and MTTF calculations: High Temperature Operating LifeTest Intrinsic(HTOL IFR, Test # 5b above)

Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

| _ | duct nilv | Package Family | Ouantity | Reiects | Extrinsic Failure Rate (PPM) | Intrinsic Failure Rate (FIT) | MTTF (hrs) |
|---|--------------|-------------------|----------|---------|---------------------------------|---------------------------------|------------|
| | JP | TSSOP | 7448 | 0 | 22 | 0.6 | 1.83 E+09 |