

Quarterly Reliability Monitoring Results

Quarters: Q1/2022 to Q4/2023

Based on structural similarity

Supplier Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		User Part Number						
		BAT54CY-Q						
		Part Description						
		Nexperia DHAM Schottky						
		SMD package						
		Test Conditions	Duration	# Lots	# Quantity	# Rejects		
	TEST							
	Pre- and Post-Stress							
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below		
		JESD22-A113						
		Bake Tamb = 125 °C	24 hours					
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours					
# A1	Preconditioning	Reflow soldering	3 cycles	1514	64430	0		
		MIL-STD-750-1						
	HTRB	M1038 Method A						
	High Temperature Reverse							
# B1	Bias	reverse voltage ^[1]	1000 hours	206	9320	0		
	TC	JESD22-A104						
# A4	Temperature Cycling	-65 °C to Tjmax, not to exceed 150°C	1000 cycles	311	14080	0		
# 42	UHAST	JESD22-A118						
# A3 or	Unbiased HAST	Tamb = 130 °C, RH = 85 %	96 hours	311	14080	0		
		JESD22-A102						
	AC	Tamb = 121 °C, RH = 100 %						
# A3 alt	Autoclave	Pressure = 205 kPa (29.7 psia)						
		JECD22 A101						
	H3TRB	JESD22-A101 Tamb = 85 °C, RH = 85%, VR = 80 % of						
# 42 -14	High Humidity High Temperature Reverse Bias	rated reverse voltage ^{[1], [2]}	1000 5	211	1.4000	0		
# A2 alt	Temperature Reverse Bias		1000 hours	311	14080	0		
	TO!	MIL-STD-750 Method 1037						
# A5	IOL Intermittent Operating Life	ton = toff, devices powered to insure ΔTj =	1000 hours	312	14120	0		
# A5	Intermittent Operating Life	100 C for 13000 cycles	1000 Hours	312	14120	U		
	RSH	JESD22-A111						
# C8	Resistance to Solder Heat		10 s	269	8070	0		
# 00	SD	200 0 = 3 0	10.5	203	0070	U		
# C10	Solderability	J-STD-002		222	6660	0		
# CIU	Solution and Colombia dis			LLL	0000	U		

^[1] The physical limitations of Schottky diodes have to be considered (thermal runaway).

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Schottky	9320	0	0,46	2,19E+09

© 2024 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com

^[2] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.