

## **Quarterly Reliability Monitoring Results**

## Quarters: Q1/2022 to Q4/2023

Based on structural similarity

Supplier Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		User Part Number BAT54W-Q Part Description											
									Nexperia DHAM	Schottky			
									SMD package				
		Test Conditions	Duration	# Lots	# Quantity	# Rejects							
			TEST										
			Pre- and Post-Stress										
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below							
		JESD22-A113											
		Bake Tamb = 125 °C	24 hours										
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours										
# A1	Preconditioning	Reflow soldering	3 cycles	1514	64430	0							
		MIL-STD-750-1											
	HTRB	M1038 Method A											
		Tj = Tjmax, Vr = 100% of max. datasheet											
# B1	Bias	reverse voltage <sup>[1]</sup>	1000 hours	206	9320	0							
		150000 4404											
	TC	JESD22-A104	1000	244	1 1000								
# A4	Temperature Cycling	-65 °C to Tjmax, not to exceed 150°C	1000 cycles	311	14080	0							
	UHAST	JESD22-A118											
# A3 <b>or</b>	Unbiased HAST	Tamb = 130 °C, RH = 85 %	-96 hours	311	14080	0							
	Olibidaed HAST	JESD22-A102											
	AC	Tamb = 121 °C, RH = 100 %											
# A3 alt	Autoclave	Pressure = 205 kPa (29.7 psia)											
# A3 ait	Addociave	11635d16 = 203 Kt d (23.7 p3id)											
	H3TRB	JESD22-A101											
	High Humidity High	Tamb = 85 °C, RH = 85%, VR = 80 % of											
# A2 alt	Temperature Reverse Bias	rated reverse voltage <sup>[1], [2]</sup>	1000 hours	311	14080	0							
	p	MIL-STD-750 Method 1037	_50000/5		000	-							
	IOL	ton = toff, devices powered to insure $\Delta T_j$ =											
# A5	Intermittent Operating Life		1000 hours	312	14120	0							
-		,		-	-	-							
	RSH	JESD22-A111											
# C8	Resistance to Solder Heat	260 °C ± 5 °C	10 s	269	8070	0							
	SD												
# C10	Solderability	J-STD-002		222	6660	0							

<sup>[1]</sup> The physical limitations of Schottky diodes have to be considered (thermal runaway).

## **Calculation of FIT and MTTF**

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1)
Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Schottky	9320	0	0,46	2,19E+09

© 2024 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com

 $<sup>\[2\]</sup>$  The maximum applied voltage is limited by test chamber set up and does not exceed 115V.