## nexperia

## **Quarterly Reliability Monitoring Results**

Quarters: Q1/2022 to Q4/2023 Based on structural similarity

Supplier		User Part Number				
Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		BZT52-B24-Q Part Description				
		SMD package				
		Test Conditions	Duration	# Lots	# Quantity	# Rejects
			TEST			
	Pre- and Post-Stress					
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below
		JESD22-A113				
	<b>B</b> C	Bake Tamb = 125 °C	24 hours			
# A1	PC Preconditioning	Soak Tamb = 85 °C, RH = 85% Reflow soldering	168 hours 3 cycles	1514	64430	0
<i>π</i> / <b>1</b>	reconditioning	MIL-STD-750-1	5 Cycles	1314	04430	0
	HTRB	M1038 Method A				
		Tj = Tjmax, VR = 80 % of rated reverse				
# B1	Bias	voltage	1000 hours	250	11400	0
		MIL-STD-750-1				
		M1038 Method B				
	SSOP	Tj = Tjmax, Iz = 100% of max. datasheet				
# B1b	Steady State Operational	reverse current	1000 hours	44	1920	0
# A4	TC Temperature Cycling	JESD22-A104 -65 °C to Tjmax, not to exceed 150°C	1000 cycles	311	14080	0
# A4	Temperature Cycling		1000 Cycles	511	14080	0
	UHAST	JESD22-A118				
# A3 <b>or</b>	Unbiased HAST	Tamb = 130 °C, RH = 85 %	96 hours	311	14080	0
		JESD22-A102				
	AC	Tamb = 121 °C, RH = 100 %				
# A3 alt	Autoclave	Pressure = 205 kPa (29.7 psia)				
	H3TRB	JESD22-A101				
" • • • ·	High Humidity High	Tamb = 85 °C, RH = 85%, VR = 80 % of	1000		1 1000	•
# A2 alt	Temperature Reverse Bias		1000 hours	311	14080	0
	IOL	MIL-STD-750 Method 1037				
# A5	INTERMITTER INTERMITTER	ton = toff, devices powered to insure $\Delta T_j$ = 100 °C for 15000 cycles	1000 hours	312	14120	0
π AJ	Internitient Operating Life	100 C 101 1000 Cycles	1000 110015	512	14120	0
	RSH	JESD22-A111				
# C8	Resistance to Solder Heat	260 °C ± 5 °C	10 s	269	8070	0
	SD					
# C10	Solderability	J-STD-002		19	6660	0

[1] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

## Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

2,68E+09
_

© 2024 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com