

## **Quarterly Reliability Monitoring Results**

## Quarters: Q1/2022 to Q4/2023

Based on structural similarity

Supplier Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		User Part Number						
		BZT52-B6V8-Q						
		Part Description						
		Nexperia DHAM						
		SMD package						
		Test Conditions	Duration	# Lots	# Quantity	# Rejects		
	<b>TEST</b> Pre- and Post-Stress							
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below		
# A1	<b>PC</b> Preconditioning	JESD22-A113 Bake Tamb = 125 °C Soak Tamb = 85 °C, RH = 85% Reflow soldering	24 hours 168 hours 3 cycles	1514	64430	0		
# B1	HTRB	MIL-STD-750-1 M1038 Method A Tj = Tjmax, VR = 80 % of rated reverse voltage	1000 hours	250	11400	0		
# B1b	SSOP Steady State Operational	MIL-STD-750-1 M1038 Method B Tj = Tjmax, Iz = 100% of max. datasheet reverse current	1000 hours	44	1920	0		
# A4	TC Temperature Cycling	JESD22-A104 -65 °C to Tjmax, not to exceed 150°C	1000 cycles	311	14080	0		
# A3 <b>or</b>	UHAST Unbiased HAST	JESD22-A118 Tamb = 130 °C, RH = 85 % JESD22-A102	—96 hours	311	14080	0		
# A3 alt	<b>AC</b> Autoclave	Tamb = 121 °C, RH = 100 % Pressure = 205 kPa (29.7 psia)						
# A2 - It	H3TRB High Humidity High	JESD22-A101 Tamb = 85 °C, RH = 85%, VR = 80 % of	1000 have	211	14000	0		
# A2 alt	Temperature Reverse Bias	MIL-STD-750 Method 1037 ton = toff, devices powered to insure ΔTj =	1000 hours	311	14080	0		
# A5	Intermittent Operating Life	, .	1000 hours	312	14120	0		
# C8	<b>RSH</b> Resistance to Solder Heat	JESD22-A111 260 °C ± 5 °C	10 s	269	8070	0		
# C10	<b>SD</b> Solderability	J-STD-002		19	6660	0		

<sup>[1]</sup> The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

## **Calculation of FIT and MTTF**

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Zener	11400	0	0,37	2,68E+09

<sup>© 2024</sup> Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com