

## **Quarterly Reliability Monitoring Results**

## Quarters: Q3/2021 to Q4/2022

Based on structural similarity

Supplier Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		User Part Number PESD12VV1BL Part Description										
								Nexperia DHAM Protection				
								MCD package				
		Test Conditions	Duration	# Lots	# Quantity	# Rejects						
			TEST									
			Pre- and Post-Stress									
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below						
		JESD22-A113										
		Bake Tamb = 125 °C	24 hours									
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours									
# A1	Preconditioning	Reflow soldering	3 cycles	211	12520	0						
		MIL-STD-750-1										
	HTRB	M1038 Method A										
	<b>.</b>	Tj = Tjmax, Vr = 100% of max. datasheet				_						
# B1	Bias	reverse voltage	1000 hours	166	10040	0						
	тс	JESD22-A104										
# A4	Temperature Cycling	-65 °C to Timax, not to exceed 150°C	1000 eveles	70	4640	0						
# A4	remperature cycling	os e to rimax, not to exceed 150 e	1000 cycles	78	4640	0						
	UHAST	JESD22-A118										
# A3 <b>or</b>	Unbiased HAST	Tamb = 130 °C, RH = 85 %		57	3420	0						
		JESD22-A102	— 96 hours									
	AC	Tamb = 121 °C, RH = 100 %										
# A3 alt	Autoclave	Pressure = 205 kPa (29.7 psia)										
		<u> </u>										
	<b>НЗТ</b> В	JESD22-A101										
	High Humidity High	Tamb = 85 °C, RH = 85%, VR = 80 % of										
# A2 alt	Temperature Reverse Bias	rated reverse voltage <sup>[1]</sup>	1000 hours	75	4460	0						
		MIL-STD-750 Method 1037										
	IOL	ton = toff, devices powered to insure $\Delta Tj$ =										
# A5	Intermittent Operating Life	100 °C for 15000 cycles	1000 hours	n.a.	n.a.	n.a.						
	RSH	JESD22-A111										
# C8	Resistance to Solder Heat	260 °C ± 5 °C	10 s	n.a.	n.a.	n.a.						
	SD											
# C10	Solderability	J-STD-002		111	1110	0						

<sup>[1]</sup> The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

## **Calculation of FIT and MTTF**

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Protection	10040	0	0,42	2,36E+09

<sup>© 2023</sup> Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com