

Quarterly Reliability Monitoring Results

Quarters: Q1/2022 to Q4/2023

Based on structural similarity

Supplier		User Part Number						
Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		PMEG3010CEH-Q						
		Part Description						
		Nexperia DHAM Schottky						
		SMD package						
		Test Conditions	Duration	# Lots	# Quantity	# Rejects		
	TEST							
	Pre- and Post-Stress							
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below		
l		JESD22-A113						
		Bake Tamb = 125 °C	24 hours					
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours					
# A1	Preconditioning	Reflow soldering	3 cycles	1514	64430	0		
		MIL-STD-750-1						
	HTRB	M1038 Method A						
	High Temperature Reverse	Tj = Tjmax, $Vr = 100%$ of max. datasheet						
# B1	Bias	reverse voltage ^[1]	1000 hours	206	9320	0		
	TC	JESD22-A104						
# A4	Temperature Cycling	-65 °C to Tjmax, not to exceed 150°C	1000 cycles	311	14080	0		
# 42	UHAST Unbiased HAST	JESD22-A118						
# A3 or	Undiased HAST	Tamb = 130 °C, RH = 85 %	- 96 hours	311	14080	0		
		JESD22-A102						
	AC	Tamb = 121 °C, RH = 100 %						
# A3 alt	Autoclave	Pressure = 205 kPa (29.7 psia)						
		JECD22 A101						
	H3TRB	JESD22-A101 Tamb = 85 °C, RH = 85%, VR = 80 % of						
# A2 - It	High Humidity High Temperature Reverse Bias	rated reverse voltage ^{[1], [2]}	1000	211	1.4000	0		
# A2 alt	Temperature Reverse Bias	·····	1000 hours	311	14080	0		
	TO:	MIL-STD-750 Method 1037						
# A5	IOL Intermittent Operating Life	ton = toff, devices powered to insure ΔTj =	1000 haur-	212	14120	0		
# AD	Intermittent Operating Life	100 °C 101 13000 cycles	1000 hours	312	14120	0		
	RSH	JESD22-A111						
# C8	Resistance to Solder Heat	260 °C ± 5 °C	10 s	269	8070	0		
# 0	SD	200 C ± 3 C	10 5	209	0070	U		
# C10	Solderability	J-STD-002		222	6660	0		
# CIU	Soluerability	J-31D-00Z		LLL	UDDU	U		

^[1] The physical limitations of Schottky diodes have to be considered (thermal runaway).

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Schottky	9320	0	0,46	2,19E+09

© 2024 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com

^[2] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.