nexperia

Quarterly Reliability Monitoring Results

Quarters: Q1/2022 to Q4/2023 Based on structural similarity

Supplier		User Part Number						
Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-0101 Test		PMEG4002EL-Q Part Description						
								Nexperia DHAM Schottky MCD package
		Test Conditions	Duration	# Lots	# Quantity # Rejects			
			TEST				,	
			Pre- and Post-Stress					
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below		
		JESD22-A113	.,					
		Bake Tamb = $125 ^{\circ}\text{C}$	24 hours					
	PC	Soak Tamb = 85 °C, RH = 85%	168 hours					
# A1	Preconditioning	Reflow soldering	3 cycles	208	9760	0		
		MIL-STD-750-1	•					
	HTRB	M1038 Method A						
		Tj = Tjmax, Vr = 100% of max. datasheet						
# B1	Bias	reverse voltage ^[1]	1000 hours	206	9320	0		
<i>"</i> D1								
	тс	JESD22-A104						
# A4	Temperature Cycling	-65 °C to Timax, not to exceed 150°C	1000 cycles	53	2400	0		
	. , ,							
	UHAST	JESD22-A118						
# A3 or # A3 alt	Unbiased HAST	Tamb = 130 °C, RH = 85 %						
		JESD22-A102	— 96 hours	53	2400	0		
	AC	Tamb = $121 ^{\circ}C$, RH = $100 ^{\circ}M$						
	Autoclave	Pressure = $205 \text{ kPa} (29.7 \text{ psia})$						
	H3TRB	JESD22-A101						
	High Humidity High	Tamb = 85 °C, RH = 85%, VR = 80 % of						
# A2 alt	Temperature Reverse Bias		1000 hours	53	2400	0		
		MIL-STD-750 Method 1037	1000 110013	55	2100	0		
	IOL	ton = toff, devices powered to insure ΔT_i =						
# A5	Intermittent Operating Life		1000 hours	49	2560	0		
,,,,,	inconnicient operating Life	100 C.0. 19000 Cycles	1000 110015	65	2300	0		
	RSH	JESD22-A111						
# C8	Resistance to Solder Heat	$260 ^{\circ}\text{C} \pm 5 ^{\circ}\text{C}$	10 s	n.a.	n.a.	n.a.		
	SD	200 0 - 5 0	10.3					
# C10	Solderability	J-STD-002		37	1110	0		
	,	des have to be considered (thermal runaway).		57	1110	U		

The physical limitations of Schottky diodes have to be considered (thermal runaway).
 The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia					
DHAM	Schottky	9320	0	0,46	2,19E+09

© 2024 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com