nexperia

Quarterly Reliability Monitoring Results

Quarters: Q1/2022 to Q4/2023

Based on structural similarity

Supplier		User Part Number						
Nexperia B.V. Name of Laboratory Assembly reliability labs Based on AEC-Q101 Test		PTVS36VP1UP-Q						
		Part Description						
		Nexperia DHAM Protection						
		SMD package						
		Test Conditions	# Quantity	# Rejects				
	TEST							
	Pre- and Post-Stress							
# E1	Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below		
		JESD22-A113 Bake Tamb = 125 °C	24 hours					
	PC	Soak Tamb = $85 ^{\circ}$ C, RH = 85%	168 hours					
# A1	Preconditioning	Reflow soldering	3 cycles	524	22940	0		
	HTRB	MIL-STD-750-1						
		M1038 Method A Tj = Tjmax, Vr = 100% of max. datasheet						
# B1	Bias	reverse voltage	1000 hours	205	9400	0		
# 01			1000 110013	205	5400	0		
	тс	JESD22-A104						
# A4	Temperature Cycling	-65 °C to Tjmax, not to exceed 150°C	1000 cycles	156	7080	0		
	UHAST	JESD22-A118						
# A3 or	Unbiased HAST	Tamb = 130 °C, RH = 85 %	— 96 hours	156	7080	0		
		JESD22-A102	50 110013					
	AC	Tamb = 121 °C, RH = 100 %						
# A3 alt	Autoclave	Pressure = 205 kPa (29.7 psia)						
		JESD22-A101						
	H3TRB High Humidity High	Tamb = $85 ^{\circ}$ C, RH = 85% , VR = 80% of						
# A2 alt	Temperature Reverse Bias		1000 hours	156	7080	0		
# A2 alt	Temperature Reverse blas	MIL-STD-750 Method 1037	1000 nours	130	7080	0		
	IOL	ton = toff, devices powered to insure ΔT_i =						
# A5	Intermittent Operating Life		1000 hours	n.a.	n.a.	n.a.		
" ירא			1000 110013		a.	n.a.		
	RSH	JESD22-A111						
# C8	Resistance to Solder Heat		10 s	56	1700	0		
	SD							
# C10	Solderability	J-STD-002		56	1700	0		

[1] The maximum applied voltage is limited by test chamber set up and does not exceed 115V.

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Reverse Bias (HTRB, Test #B1) Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia DHAM	Protection	9400	0	0,45	2,21E+09

© 2024 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

nexperia.com