

Quarterly Reliability Monitoring Results

Quarters: Q1/2023 to Q4/2024

Based on structural similarity

Supplier		User Part Number				
Nexperia B.V.		TL431AMFDT-Q				
Name of Laboratory		Part Description				
Assembly reliability labs		Nexperia DHAM Bipolar Analog Power SMD package				
Based on AEC-Q100 Test		Test Conditions	Duration	# Lots	# Quantity	# Rejects
# E1	TEST Pre- and Post-Stress Electrical Test	Tamb = 25 °C	N/A	see below	all parts	see below
# A1	PC Preconditioning	JESD22-A113 Bake Tamb = 125 °C Soak Tamb = 85 °C, RH = 85% Reflow soldering	24 hours 168 hours 3 cycles	149	3840	0
# A2	THB Temperature Humidity Bias	JESD22-A101 Tamb = 85 °C, RH = 85%, Vref = 0 V, VKA = 36 V	1000 hours	24	960	0
# A3	UHST Unbiased HAST or	JESD22-A118 Tamb = 130 °C, RH = 85 %	96 hours	24	960	0
	AC Autoclave	JESD22-A102 Tamb = 121 °C, RH = 100 % Pressure = 205 kPa (29.7 psia)				
# A4	TC Temperature Cycling	JESD22-A104 -65 °C to +150 °C	1000 cycles	24	960	0
# A5	IOL Intermittent Operating Life	MIL-STD-750 Method 1037 ton = toff = 2 minutes, Ptot = 250 mW to insure ΔTj = 100 °C for 15000 cycles	1000 hours	24	960	0
# B1	HTOL High Temperature Operating Life	Tamb = 150 °C, Vref = 0 V, VKA = 36 V	1000 hours	45	1800	0
# C3	RSH Resistance to Solder Heat	JESD22-A111 / JESD22-B106 260 °C ± 5 °C	10 s	32	960	0
	SD Solderability	JESD22-B102 245 °C ± 5 °C		421	12630	0

Calculation of FIT and MTTF

Test considered for FIT calculation: High Temperature Operating Life (HTOL, Test #B1)

Confidence level 60%, derated to 55 °C, activation energy 0.7 eV, test time 168 to 1000 hours

Wafer Fab	Technology	Quantity	Rejects	Failure Rate (FIT)	MTTF (hrs)
Nexperia DHAM	Bipolar Analog Power	1800	0	2,36	4,24E+08

© 2025 Nexperia B.V.

All information hereunder is per Nexperia's best knowledge. This document does not provide for any representation or warranty express or implied by Nexperia. In case Nexperia has tested the product, this documentation reflects the outcome of the analysis of the actually tested parts only.

[nexperia.com](https://www.nexperia.com)